

# Sky Rocket™



**COVERSTOCK:** R2S™ Pearl Reactive

**WEIGHT BLOCK:** Booster™ Core

**LIGHT WEIGHT BLOCK:** Modified Centripetal™ Core

**FACTORY FINISH:** 1500-grit Polished

**BALL COLOR:** Sky Blue/Charcoal

**DUROMETER:** 73-75 Rex D-scale

**FLARE POTENTIAL:** 4" - 5" (Medium-High)

**FRAGRANCE:** Sangria

**WEIGHTS:** 12-16 lbs.

Lbs.	RG	Diff.	Weight Block
16	2.53	0.044	
15	2.54	0.046	
14	2.55	0.048	
13	2.59	0.045	
12	2.65	0.035	

## Resurfacing to a 1500-grit Polished Factory Finish

Resurface to the original factory finish using a ball spinner.

1. 500-grit Abralon® - Sand for 30 seconds on all four sides with firm pressure.
2. 1000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
3. 2000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
4. 4000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
5. Storm Step Two™ - Polish lightly for 15 seconds each side.

Storm recommends using the suggested cleaner/polish daily. Storm also recommends touching up the surface with only the final step every 20 games and resurfacing completely every 30-50 games.



Use Reacta Shine™ Reactive Polish and Cleaner after every session.