

Tropical Heat™ Orange/Purple



COVERSTOCK: Reactor™ Pearl Reactive

WEIGHT BLOCK: Turbine™ Core B

FACTORY FINISH: 1500-grit Polished

BALL COLOR: Orange/Purple

DUROMETER: 74-76 Rex D-scale

FLARE POTENTIAL: 3" - 4" (Medium)

FRAGRANCE: Creamsicle

WEIGHTS: 10-16 lbs.

Lbs.	RG	Diff.
16	2.53	0.040
15	2.55	0.038
14	2.58	0.035
13	2.59	0.045
12	2.65	0.035

Resurfacing to a 1500-grit Polished Factory Finish

Resurface to the original factory finish using a ball spinner.

1. 500-grit Abralon® - Sand for 30 seconds on all four sides with firm pressure.
2. 1000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
3. 2000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
4. 4000-grit Abralon® - Sand for 20 seconds on all four sides with light pressure.
5. Storm Step Two™ - Polish lightly for 15 seconds each side.

Storm recommends using the suggested cleaner/polish daily. Storm also recommends touching up the surface with only the final step every 20 games and resurfacing completely every 30-50 games.



Use Reacta Shine™ Reactive Polish and Cleaner after every session.