

Clear Storm™



COVERSTOCK: Clear Polyester

WEIGHT BLOCK: Traditional 3-piece Core

FACTORY FINISH: 3500-grit Polished

BALL COLOR: White / Navy

DUROMETER: 82-84 Rex D-scale

FLARE POTENTIAL: 1" - 2" (Low)

WEIGHTS: 12-16 lbs.

Lbs.	RG	Diff.	Weight Block
16	2.68	0.006	
15	2.69	0.006	
14	2.69	0.006	
13	2.71	0.005	
12	2.72	0.005	

Resurfacing to a 3500-grit Factory Finish

Resurface to the original factory finish using a ball spinner.

1. 500-grit Abralon™ pad - Sand for 15 seconds on all four sides.
2. 1000-grit Abralon™ pad - Sand for 20 seconds on all four sides.
3. 2000-grit Abralon™ pad - Sand for 25 seconds on all four sides.
4. 4000-grit Abralon™ pad - Sand for 30 seconds on all four sides.
5. Storm® Xtra Shine™ - Polish for 30 seconds on two sides.

Storm recommends using the suggested cleaner/polish daily. Storm also recommends touching up the surface with only the final step every 20 games and resurfacing completely every 30-50 games.



Use Xtra Clean™ after every session.